Preservation and Care of Philatelic Materials

Subsidiary Page 20 Stock Sheets

The following test results by the Salm Foundation indicate that most stock sheets have a pH of less than 7. All are in the acceptable range.

Stockbook	by Lighthouse	рН 5.78
Black Sheets	by Hagner	рН 6.56
White 8419	by Davo	рН 6.69
White Sheets	by Hagner	рН 6.72
Manilla sheets	by Master	рН 7.88
White manilla strips	by Harco	рН 8.23

Only three album page interleaves were tested. All proved satisfactory for conservation purposes:

#3311	by Stanley Gibbons	рН 5.26
#332	by Stanley Gibbons	рН 5.35
interleaves	by Harco	рН 5.88